

NT93-s

Non-Silicone Thermal Conductive RF Absorber Pad

LiPOLY NT93-s is a thermally conductive absorber based upon soft magnetic materials dispersed in a non-silicone resin. It has a thermal conductivity of 3.0 W/m*K and dissipates electromagnetic radiation rapidly to mitigate against EMI issues.

FEATURES

- / Thermal conductivity: 3.0 W/m*K
- / Excellent absorption characteristics
- / Naturally tacky
- / Reworkable

TYPICAL APPLICATION

- / IC, CPU, MOS, LED, M/B, Heat sink
- / LCD-TV, Notebook PC, PC, Telecom device, Wireless hub
- / DDR II module, DVD applications, Hand-set applications
- / 5G base station & infrastructure
- / EV electric vehicle

SPECIFICATIONS

- / Sheet form
- / Die-cut parts


FREQUENCY APPLICATION

- 2.4 GHz Wi-Fi Router , Bluetooth
- 3.5 GHz 5G Mobile Networks
- 5.0 GHz Wi-Fi Router
- 6.0 GHz Wi-Fi Router
- 12~18 GHz Low Earth Orbit (LEO) System
- 28 GHz 5G Mobile Networks
- 39 GHz 5G Mobile Networks


TYPICAL PROPERTIES

PROPERTY	NT93-s	TEST METHOD	UNIT
Color	Dark Gray	Visual	-
Surface tack 2-side/1-side	2	-	-
Thickness	Customized	ASTM D374	mm
Density	3.7	ASTM D792	g/cm ³
Hardness	65	ASTM D2240	Shore OO
Application temperature	-60~125	-	°C
ROHS & REACH	Compliant	-	-
COMPRESSION@1.0mm			
Deflection @10 psi	6	ASTM D5470 modify	%
Deflection @20 psi	8	ASTM D5470 modify	%
Deflection @30 psi	13	ASTM D5470 modify	%
Deflection @40 psi	21	ASTM D5470 modify	%
Deflection @50 psi	32	ASTM D5470 modify	%
EMI Attenuation @1.0mm			
EMI attenuation@ 2.4 GHz	12	ASTM D4935 modify	dB/cm
EMI attenuation@ 3.5 GHz	14	ASTM D4935 modify	dB/cm
EMI attenuation@ 5.0 GHz	29	ASTM D4935 modify	dB/cm
EMI attenuation@ 6.0 GHz	25	ASTM D4935 modify	dB/cm
EMI attenuation@ 12 GHz	60	ASTM D4935 modify	dB/cm
EMI attenuation@ 18 GHz	71	ASTM D4935 modify	dB/cm
EMI attenuation@ 28 GHz	112	ASTM D4935 modify	dB/cm
EMI attenuation@ 39 GHz	68	ASTM D4935 modify	dB/cm
ELECTRICAL			
Surface resistivity	>10 ¹¹	ASTM D257	Ohm
Volume resistivity	>10 ¹⁰	ASTM D257	Ohm-m
THERMAL			
Thermal Conductivity	3.0	ASTM D5470	W/m*K
Thermal impedance@10 psi	0.632	ASTM D5470	°C-in ² / W
Thermal impedance@20 psi	0.581	ASTM D5470	°C-in ² / W
Thermal impedance@30 psi	0.539	ASTM D5470	°C-in ² / W
Thermal impedance@40 psi	0.493	ASTM D5470	°C-in ² / W
Thermal impedance@50 psi	0.436	ASTM D5470	°C-in ² / W

Attenuation



Thermal Resistance vs. Pressure vs. Deflection



Note: All specifications provided by LiPOLY are subject to change without notice. The test methods used for LiPOLY. Property values provided in this document are not for product specifications or guaranteed. This document does not guarantee the performance and quality required for the purchaser's specific purpose. The purchaser needs to evaluate and verify the safety before using the material. We strongly recommend the purchaser pre-test the product and verify the performance of the product under the purchaser's specific conditions. Liability and use of the product are the responsibility of the end user. LiPOLY makes no warranty as to the suitability, merchantability, or non-infringement of any LiPOLY material or product for any specific or general uses. LiPOLY shall not be liable for incidental or consequential damages of any kind. All LiPOLY products are sold in accordance with the LiPOLY Terms and Conditions in effect at the time of purchase and a copy of which will be furnished upon request. All rights reserved, including LiPOLY trademarks or registered trademarks of LiPOLY or its affiliates. Statements concerning possible or suggested uses made herein shall not be relied upon or be construed as a guaranty of patent infringement. Copyright 2024 LiPOLY.