

BS75K-s

Exceptionally Soft Thermal Conductive Gel Pad

LiPOLY BS75K-s is an ultra-soft thermally conductive gel pad with a thermal conductivity of 3.0 W/m*K. BS75K-s offers excellent compression under minimal force with high recovery characteristics. This product can be supplied as standard sheets, custom die-cuts or custom molded parts.

■ FEATURES

- / Thermal conductivity: 3.0 W/m*K
- / High compression rate
- / Low thermal impedance
- / High recovery
- / Available in a range of thicknesses


■ TYPICAL APPLICATION

- / Between CPU and heat sink
- / Between a component and heat sink
- / Notebook computers
- / Power supplies
- / High speed mass storage drives
- / Telecommunication hardware
- / 5G base station & infrastructure
- / EV electric vehicle

SPECIFICATIONS

/ Roll form / Sheet form / Die-cut parts






■ TYPICAL PROPERTIES

- TITICAL FROI ERTIES			
PROPERTY	BS75K-s	TEST METHOD	UNIT
Color	Dark Gray	Visual	-
Surface tack 2-side/1-side	2	-	-
Thickness	Customized	ASTM D374	mm
Density	2.6	ASTM D792	g/cm³
Hardness	18	ASTM D2240	Shore OO
Application temperature	-60~180	-	°C
ROHS & REACH	Compliant	-	-
COMPRESSION@1.0mm			
Deflection @10 psi	35	ASTM D5470 modify	%
Deflection @20 psi	39	ASTM D5470 modify	%
Deflection @30 psi	43	ASTM D5470 modify	%
Deflection @40 psi	46	ASTM D5470 modify	%
Deflection @50 psi	48	ASTM D5470 modify	%
ELECTRICAL			
Dielectric breakdown	12	ASTM D149	KV/mm
Surface resistivity	>1010	ASTM D257	Ohm
Volume resistivity	>1011	ASTM D257	Ohm-m
THERMAL			
Thermal conductivity	3.0	ASTM D5470	W/m*K
Thermal impedance@10 psi	0.562	ASTM D5470	°C-in²/ W
Thermal impedance@20 psi	0.543	ASTM D5470	°C-in²/ W
Thermal impedance@30 psi	0.504	ASTM D5470	°C-in²/ W
Thermal impedance@40 psi	0.485	ASTM D5470	°C-in²/ W
Thermal impedance@50 psi	0.463	ASTM D5470	°C-in²/ W

Thermal Impedance vs. Pressure vs. Deflection



Note: All specifications provided by LiPOLY are subject to change without notice. The test methods used by LiPOLY are based on the TIM Tester method and ASTM D5470 test method. These test methods are used as the definition standards for LiPOLY Property values provided in this document are not for product specifications or guaranteed. This document does not guarantee the performance of the product and verify the safety before using the material. We strongly recommend the purchaser pre-test the product and verify the performance of the product and verify the performance o